



TECHNICAL DATA SHEET

Crown Battery Mfg. Co. • Fremont, Ohio USA
419-334-7181 • FAX 419-334-7124

CR-210

Commercial Deep Cycle Battery

Crown Battery Manufacturing Company offers a complete lineup of high-performing and low-maintenance commercial deep cycle batteries produced in standard BCI industry profiles for voltage, electrical capacity and physical dimension. Crown Battery's innovative and proven deep cycle product design makes it the battery of choice for many tough commercial battery applications, including commercial floor care and aerial access equipment, electric motorcars, personnel carriers, material handling equipment and photovoltaic systems.

SPECIFICATIONS


| | | | |
|--------------------------|------------|--------------------|----------|
| Nominal Voltage | | 12 Volts | |
| Amp Hour Capacity | | 210 (C20) | 175 (C5) |
| Reserve Capacity Minutes | | 110 @ 75 Amperes | |
| Physical Characteristics | Length | 15.50" | 394 mm |
| | Width | 7.00" | 178 mm |
| | Height | 14.50" | 368 mm |
| | Wet Weight | 130 Lbs | 59.0 Kgs |
| Terminal Options | | A/T, C/T, S/T, Z/T | |

ELECTRICAL SPECIFICATIONS

| | | | |
|---|--------------|---------|----------|
| Amp Hour Capacity | 20 Hour Rate | 10.50 A | 210 Ah |
| | 10 Hour Rate | 17.70 A | 177 Ah |
| | 5 Hour Rate | 35.00 A | 175 Ah |
| | 2 Hour Rate | 57.50 A | 115 Ah |
| Internal Resistance | 80 F | 27 C | 9.5 mOhm |
| Capacity affected by Temperature (20 Ah Rate) | 104 F | 40 C | 102% |
| | 80 F | 27 C | 100% |
| | 32 F | 0 C | 65% |



Available Terminals



| | |
|--|---|
| <i>Cover Style:</i> | Exposed Vent Opening |
| <i>Cover Vent Style:</i> | Quarter-Turn Bayonet Style |
| <i>Container and Cover Material:</i> | Black Polypropylene |
| <i>Case to Cover Seal Method:</i> | Heat Seal |
| <i>Inner-Cell Connector Type:</i> | Through Partition Weld |
| <i>Plate Lug to Collector Bar Fusion Method:</i> | Inverted Automatic Cast-On |
| <i>Number of Plates per Battery:</i> | 78 Plates |
| <i>Positive Grid Material:</i> | Antimony Lead Alloy |
| <i>Positive Grid Design:</i> | Z ³ Horizontal Pellet |
| <i>Positive Plate Dimension:</i> | 5.750" x 9.750" x 0.120" 146mm x 248mm x 3.0mm |
| <i>Negative Grid Material:</i> | Antimony Lead Alloy |
| <i>Negative Grid Design:</i> | Z ³ Horizontal Pellet |
| <i>Negative Plate Dimension:</i> | 5.750" x 9.750" x 0.085" 146mm x 248mm x 2.2mm |
| <i>Separator Type:</i> | Microporous Polyethylene Envelope with Glass |

Visit our website at
www.crownbattery.com

Crown Battery Manufacturing's team of research and development engineers welcome the opportunity to discuss your technical requirements during the design and specification stage. To access this technical assistance, please contact Crown Battery Manufacturing's Customer Service Department at 800.487.2879 / sales@crownbattery.com / FAX 419.334.7124.

Recommended Charge Profile


Following discharge, constant current charge the CR-210 battery at 25 amperes until the battery voltage measures 2.42 volts per cell (14.52 volts open circuit voltage).

The constant voltage charge phase begins after the gassing point (2.42 VPC) is achieved. During the constant voltage phase, the charger voltage limit is regulated to the gassing point of 2.42 volts per cell, while the input current is allowed to gradually fall off. When the input current drops to the finish rate setting of 7 amperes, the charging phase will change from constant voltage to a sustained 7 ampere constant current mode. The charging cycle will be terminated 3.5 to 5 hours from the gassing point, with factors such as ambient temperature, battery condition and depth of discharge affecting the charge completion time.

The CR-210 battery should receive a full recharge following the completion of each discharge, along with a weekly equalization service charge. During the equalization charge cycle the finish rate charge time is extended by 3 hours (6.5 to 8 hours from the gassing point).

The charge factor of the standard recharge should be equal to or greater than 1.07 (107%). The charge factor of the equalizing cycle should be equal to or greater than 1.15 (115%).

Please contact Crown Battery Manufacturing Company's engineering department with any questions regarding this charge profile specification.



The Power Behind Performance

Data are nominal and should not be construed as maximum or minimum values for specification or for final design. Data for this product type may vary from that shown herein.