



TECHNICAL DATA SHEET

Crown Battery Mfg. Co. • Fremont, Ohio USA
419-334-7181 • FAX 419-334-7124

CR-235

Commercial Deep Cycle Battery

Crown Battery Manufacturing Company offers a complete lineup of high-performing and low-maintenance commercial deep cycle batteries produced in standard BCI industry profiles for voltage, electrical capacity and physical dimension. Crown Battery's innovative and proven deep cycle product design makes it the battery of choice for many tough commercial battery applications, including commercial floor care and aerial access equipment, electric motorcars, personnel carriers, material handling equipment and photovoltaic systems.

SPECIFICATIONS


Nominal Voltage		6 Volts	
Amp Hour Capacity		235 (C20)	195 (C5)
Reserve Capacity Minutes		125 @ 75 Amperes	
Physical Characteristics	Length	10.25"	260 mm
	Width	7.13"	181 mm
	Height	10.50"	267 mm
	Wet Weight	70 Lbs	32.2 Kgs
Terminal Options		A/T, C/T, S/T, Z/T	

ELECTRICAL SPECIFICATIONS

Amp Hour Capacity	20 Hour Rate	11.75 A	235 Ah
	10 Hour Rate	22.30 A	223 Ah
	5 Hour Rate	35.80 A	179 Ah
	2 Hour Rate	73.00 A	146 Ah
Internal Resistance	80 F	27 C	5.1 mOhm
Capacity affected by Temperature (20 Ah Rate)	104 F	40 C	102%
	80 F	27 C	100%
	32 F	0 C	65%



Available Terminals



<i>Cover Style:</i>	Exposed Vent Opening
<i>Cover Vent Style:</i>	Quarter-Turn Bayonet Style
<i>Container and Cover Material:</i>	Polypropylene Plastic
<i>Case to Cover Seal Method:</i>	Heat Seal
<i>Inner-Cell Connector Type:</i>	Through Partition Weld
<i>Plate Lug to Collector Bar Fusion Method:</i>	Inverted Automatic Cast-On
<i>Number of Plates per Battery:</i>	57 Plates
<i>Positive Grid Material:</i>	Antimony Lead Alloy
<i>Positive Grid Design:</i>	Z ³ Horizontal Pellet
<i>Positive Plate Dimension:</i>	6.250" x 6.750" x 0.105" 159mm x 171mm x 2.7mm
<i>Negative Grid Material:</i>	Antimony Lead Alloy
<i>Negative Grid Design:</i>	Z ³ Horizontal Pellet
<i>Negative Plate Dimension:</i>	6.250" x 6.750" x 0.080" 159mm x 171mm x 2.0mm
<i>Separator Type:</i>	Microporous Rubber with Glass Mat

Visit our website at
www.crownbattery.com

Crown Battery Manufacturing's team of research and development engineers welcome the opportunity to discuss your technical requirements during the design and specification stage. To access this technical assistance, please contact Crown Battery Manufacturing's Customer Service Department at 800.487.2879 / sales@crownbattery.com / FAX 419.334.7124.

Recommended Charge Profile


Following discharge, constant current charge the CR-200 battery at 25 to 30 amperes until the battery voltage measures 2.42 volts per cell (7.26 volts open circuit voltage).

The constant voltage charge phase begins after the gassing point (2.42 VPC) is achieved. During the constant voltage phase, the charger voltage limit is regulated to the gassing point of 2.42 volts per cell, while the input current is allowed to gradually fall off. When the input current drops to the finish rate setting of 9 amperes, the charging phase will change from constant voltage to a sustained 9 ampere constant current mode. The charging cycle will be terminated 3.5 to 5 hours from the gassing point, with factors such as ambient temperature, battery condition and depth of discharge affecting the charge completion time.

The CR-235 battery should receive a full recharge following the completion of each discharge, along with a weekly equalization service charge. During the equalization charge cycle the finish rate charge time is extended by 3 hours (6.5 to 8 hours from the gassing point).

The charge factor of the standard recharge should be equal to or greater than 1.07 (107%). The charge factor of the equalizing cycle should be equal to or greater than 1.15 (115%).

Please contact Crown Battery Manufacturing Company's engineering department with any questions regarding this charge profile specification.



The Power Behind Performance

Data are nominal and should not be construed as maximum or minimum values for specification or for final design. Data for this product type may vary from that shown herein.